



**HEAD OFFICE**  
22 Park Drive  
Dandenong VIC 3175

Phone: **(03) 9768 4900**  
Fax **(03) 9768 4999**  
[www.unitex.com.au](http://www.unitex.com.au)

**NSW OFFICE**  
14 Artisan Road  
Seven Hills NSW 2147

Phone: **(02) 9838 0911**  
Fax **(02) 9838 9555**  
[www.unitex.com.au](http://www.unitex.com.au)

**RENDER WAREHOUSE**  
1346 North Road  
Oakleigh South VIC 3167

Phone: **1800 RENDER**  
Fax **(03) 9544 3620**  
[www.render.com.au](http://www.render.com.au)

## Technical Data Sheet

### Unitex® DryPoly Render

Blended dry powder polymer modified cement based render for thin trowel-applied one coat applications with the highest adhesion and flexibility that Unitex® offers with dry powder renders. Unitex® DryPoly Render is recommended for covering new and old brickwork, rough concrete, bare Expanded PolyStyrene (EPS) wall cladding boards and Fibrous Cement Sheeting (FRC) as a filling and levelling compound.

#### Description

Unitex® DryPoly Render is a cement-based blended powder that when mixed thoroughly with water, can be trowel applied in typical thicknesses up to 3 mm over masonry surfaces such as new and old bricks and concrete block-work and more difficult substrates such as bare or coated EPS boards and FRC sheets.

For the discerning project managers, builders and applicators, Unitex® DryPoly Render assists your project as follows:

Trowels on easily and smoothly in thin layers.

Is the strongest adhering polymer-modified cement based render in the Unitex® range.

Is more waterproof than conventional render.

Easily prepared. Just add water and drill to your preferred consistency.

Is ideal for patching, leveling, skim coating and restoration of damaged surfaces.

Consistent quality.

After drying, can be overcoated with a tinted Unitex Applied Texture Finish.

Is readily available in paper sacks individually or on 60 sack pallets.

Is manufactured by Unitex® in Australia.

#### Uses

Unitex® DryPoly Render is a trowel applied filling and leveling compound suitable for application on dry, non-porous and difficult substrates. Unitex® DryPoly Render is also used for patching, leveling, skim coating and restoration of damaged surfaces. Unitex® DryPoly Render is the strongest adhering dry powder render from the Unitex® range of specialty render products.

Unitex® DryPoly Render is designed for use over FRC sheeting as a levelling preparation skim coat and is trowel applied prior to overcoating with Texture from the Unitex® Applied Finishes range. As a blended cement based powder, the product must be mixed with water and mechanically stirred with a drill until the desired consistency of slurry has been achieved (see later). With a trowel, the slurry must be applied and trowel finished with speed as this type of render dries from the surface first. Unitex® DryPoly Render is recommended in coatings of 3-5 mm thickness as any higher builds are difficult both to apply and to dry.

Unitex® DryPoly Render is designed to be overcoated with Unitex Applied Finishes such as factory tinted Uni-Trowel Décor 146, 155, 333 or 777 "wet" textures or Uni-Cote 846 or 855 dry powder textures. After the texture is dry, a suitable factory tinted topcoat such as Uni-PTC can be applied for added protection against weather effects.

Unitex® DryPoly Render is supplied in ready-to-use 19 kg bags. Each bag allows up to 15 litres of wet render to be prepared by mixing the bag contents with approximately 4-5 litres of clean water and drilling for homogeneity.

Coverage per bag depends on the desired thickness of the render and at a low-build thickness of 2-3 mm., coverage of approximately 8-10 m<sup>2</sup> can be expected.



**HEAD OFFICE**  
22 Park Drive  
Dandenong VIC 3175

Phone: (03) 9768 4900  
Fax (03) 9768 4999  
[www.unitex.com.au](http://www.unitex.com.au)

**NSW OFFICE**  
14 Artisan Road  
Seven Hills NSW 2147

Phone: (02) 9838 0911  
Fax (02) 9838 9555  
[www.unitex.com.au](http://www.unitex.com.au)

**RENDER WAREHOUSE**  
1346 North Road  
Oakleigh South VIC 3167

Phone: 1800 RENDER  
Fax (03) 9544 3620  
[www.render.com.au](http://www.render.com.au)

## Application Instructions

### Substrates

Masonry surfaces such as new or old brickwork, concrete block-work, bare EPS wall cladding boards and factory coated Uni-Base Board wall cladding boards, and Fibrous Reinforced Cement (FRC) sheets. .

### Substrate condition

Before application of any render, the substrate must be clean, dry, cured and free of any dust and debris. This means that any loose or damaged substrate must be removed, or patched and repaired, and any moisture must also evaporate out prior to Unitex® DryPoly Render being trowelled onto the substrate.

Ensure that the surface is clean and dry. All surfaces must be free of efflorescence, grease, oil, mould, dirt, dust, release agents, bond-breakers or other contaminants that may interfere with adhesion. Pre-painted substrates must be wire brushed back to the bare substrate.

Adequate expansion joints are required to minimize cracking on the surface of the render. Location of the expansion joints is the responsibility of the Builder or Head Contractor. Unitex® recommends expansion joints to every elevation and between different substrates to allow for building movements and stresses. If such expansion joints are not provided, cracking due to movement of the substrate may occur. This is in no way indicative of faulty material. Rather it indicates sub-standard building practice.

All substrates must be dry before render is applied and conversely, all render surfaces must be dry before being over-coated. Unitex recommends testing surface dryness with a Moisture Meter (such as Protimeter) where the WME (Wood Moisture Equivalent) must be lower than 15 %.

Note: A test area of the complete Unitex® system must always be provided by the applicator for the Builder and Specifier approval.

Always contact Unitex® for specific substrate specifications.

### Weather Conditions

If temperatures are less than 8 °C or greater than 30°C, Unitex® DryPoly Render should not be applied to a wall.

Freshly applied Unitex® DryPoly Render must be protected from rain, other sources of moisture and frosts for at least 48 hours.

### Mixing

As a cement-containing blended powder, Unitex® DryPoly Render must be thoroughly mixed with clean, potable water to a homogenous slurry prior to application. As the cement cures, the slurry will get thicker with time until it is no longer useable. The pot life is about 3 hours in ambient conditions.

Mechanical stirrers are recommended for mixing powder into water. Whilst the water content and flow of the slurry should vary slightly for different weather conditions (try for a little more water on days of higher temperatures), a good guide is to use 3 volumes of Unitex® DryPoly Render to one volume of water, that is, use approx. 4.5 litres of water to 1 bag of render. Unitex® DryPoly Render must always be mixed into water: not the other way around. Note that there is a useable application time (pot life) of about 3 hours before the slurry is no longer workable. Addition of too much water will result in shrinkage and cracking.

### Application on FRC sheet

Apply the mixed Unitex® DryPoly Render to the sheet gaps and embed the pre-cut 50 mm alkali resistant Uni-Mesh along the sheet gaps.

Skim coat with Unitex® DryPoly Render over the whole FRC sheet surface with a steel or perspex trowel to a depth of approximately 2-3 mm. If studs behind the sheets are uneven then use Unitex® DryPoly Render a little thicker to feather out the worst of the unevenness.

When Unitex® DryPoly Render is through dry and cured for a minimum of 48 hours (in temperate conditions), overcoat with any of the Unitex Applied Finishes.

The system requires a coating if Uni-Flex Membrane or 2 coats of Uni-PTC® to be roller coated to provide protection against solar and weather effects.

### Drying



**HEAD OFFICE**

22 Park Drive  
Dandenong VIC 3175

Phone: **(03) 9768 4900**  
Fax **(03) 9768 4999**  
[www.unitex.com.au](http://www.unitex.com.au)

**NSW OFFICE**

14 Artisan Road  
Seven Hills NSW 2147

Phone: **(02) 9838 0911**  
Fax **(02) 9838 9555**  
[www.unitex.com.au](http://www.unitex.com.au)

**RENDER WAREHOUSE**

1346 North Road  
Oakleigh South VIC 3167

Phone: **1800 RENDER**  
Fax **(03) 9544 3620**  
[www.render.com.au](http://www.render.com.au)

NON DANGEROUS GOODS

**Manufacturer's Details**

Company	Unitex Granular Marble Pty Ltd 22 Park Drive Dandenong, Vic. 3175 Australia
Telephone	+61 3 9768 4900
Telefax	+61 3 9768 4999
Website	<a href="http://www.unitex.com.au">www.unitex.com.au</a>
Date issued	01 November 2013

This information contained herein relates only to the specific material identified. Unitex Granular Marble Pty Ltd believes that such information is accurate and reliable as of the date of this Technical Data Sheet, but no representation, guarantee or warranty, expressed or implied, is made to the accuracy, reliability or completeness of the information. Unitex urges persons receiving this information to make their own determination as to the information's suitability and completeness for their particular application.