



HEAD OFFICE
22 Park Drive
Dandenong VIC 3175

Phone: (03) 9768 4900
Fax (03) 9768 4999
www.unitex.com.au

NSW OFFICE
14 Artisan Road
Seven Hills NSW 2147

Phone: (02) 9838 0911
Fax (02) 9838 9555
www.unitex.com.au

RENDER WAREHOUSE
1346 North Road
Oakleigh South VIC 3167

Phone: 1800 RENDER
Fax (03) 9544 3620
www.render.com.au

Technical Data Sheet

Unitex® BBR 8.5kg Render

Blended dry powder render for trowel application on both factory coated and applicator prepared Expanded PolyStyrene (EPS) cladding boards. Unitex® BBR 8.5 kg Render is NOT SUITABLE for direct application onto bare EPS cladding boards.

Description

Unitex® BBR 8.5 kg Render is a cement-based blended light weight powder that when mixed thoroughly with water, can be trowel applied in typical thicknesses of 6-16 mm over factory coated and applicator prepared Expanded PolyStyrene (EPS) cladding boards.

For project managers, builders and applicators, Unitex® BBR 8.5 kg Render assists your project as follows:

Is less than half the density of Unitex® Base Board Render and can be applied in a single pass to double the thickness of Unitex Base Board Render without sagging.

Provides a high build thickness of render to EPS cladding and thus fulfills a leveling and straightening function needed for a true and level wall.

Provides an exceptionally high build thickness of render to EPS cladding and thus provides structural stability, impact resistance and protection against bushfire fronts and weather effects, including rain and wind. These properties are the Performance Requirements that are expected from exterior walls of homes and buildings.

Trowels on easily and smoothly in thick layers.

Is a polymer-modified cement based render that adheres strongly with cement-modified polymer-based renders such as Unitex® Polymer Render as used directly onto bare EPS cladding boards and also onto factory coated Uni-Base Board EPS cladding boards..

Is more waterproof than conventional render.

Easily prepared. Just add water and drill to your preferred consistency.

Consistent quality.

After drying, can be overcoated with a tinted Unitex Applied Texture Finish.

Is readily available in paper sacks individually or on 60 sack pallets.

Is manufactured by Unitex in Australia.

Is an integral component of the Unitex® Base Board System of EPS cladding that is BRANZ Approved and complies with CodeMark.

For applications where upper level Bushfire Attack Levels e.g. BAL-19.5, BAL-29 and BAL-40, are required, Unitex recommends the lightweight product, Unitex® "BBR 8.5 kg" to be used. Independent testing authorities have confirmed that with the recommended thickness of 6-8 mm of Unitex® BBR 8.5 mm Render in the Unitex Base Board System, the Performance Requirements for BAL-29 can be achieved and with 12-14 mm Unitex® BBR 8.5 kg Render, BAL-40 was successfully achieved. See Unitex brochures for details on achieving upper level BAL ratings for your home and buildings.

Uses

Unitex® BBR 8.5 kg Render is specially formulated as a light weight render to strongly adhere to applicator prepared EPS board cladding, or to pre-coated Uni-Base Board EPS board cladding. Prior to applying Unitex® BBR 8.5 kg Render, the applicator must prepare bare EPS board by meshing the surface with alkali resistant coated glass fibre mesh and coating with 2-3 mm Unitex® Polymer Render (with 5-10 % added cement). For better, more consistent results, Unitex® meshes and coats EPS

**HEAD OFFICE**

22 Park Drive
Dandenong VIC 3175

Phone: **(03) 9768 4900**
Fax **(03) 9768 4999**
www.unitex.com.au

NSW OFFICE

14 Artisan Road
Seven Hills NSW 2147

Phone: **(02) 9838 0911**
Fax **(02) 9838 9555**
www.unitex.com.au

RENDER WAREHOUSE

1346 North Road
Oakleigh South VIC 3167

Phone: **1800 RENDER**
Fax **(03) 9544 3620**
www.render.com.au

boards in a factory controlled process and makes this product available to builders as Uni-Base Board in thicknesses of 50, 75 and 100 mm of EPS.

Together with a number of Unitex® components, Unitex® BBR 8.5 kg Render is an integral part of the Unitex® Base Board System for EPS wall cladding applications. The Unitex® Base Board System is BRANZ Appraised, conforms with CodeMark and has a BRAC Certificate which means that recognized independent authorities attest that the product system complies with the Performance Requirements of the Building Code of Australia. Bushfire Attack Levels of BAL-29 and BAL-40 that conform with Australian Standard AS 1530.8.1-2007 are achievable with Unitex Base Board System EPS cladding containing Unitex® BBR 8.5 kg Render at thicknesses of 6-8 mm and 12-14 mm respectively. These render thicknesses are achieved in a single pass application with Unitex® BBR 8.5 kg Render and this saves the applicator several days of drying time.

Unitex® BBR 8.5 kg Render is cement based and polymer modified for water resistance and strong adhesion. The product is trowel applied and suitable for a thick one coat application on Uni-Base Board EPS cladding. The product is workable at thicknesses of approximately 6-16 mm.

To complete the finishing system, Unitex® BBR 8.5 kg Render is overcoated with Unitex Applied Finishes such as factory tinted Uni-Trowel Décor 146, 155, 333 or 777 "wet" textures or Uni-Cote 846 or 855 dry powder textures. After the texture is dry, a suitable factory tinted topcoat such as Uni-PTC can be applied for added protection against weather effects. Drying times between coats of at least 72 hours must be observed.

Unitex® BBR 8.5 kg Render is supplied in ready-to-use 8.5 kg bags. Each bag allows up to 15 litres of wet render to be prepared by mixing the bag contents with approximately 4-5 litres of clean water and drilling for homogeneity.

Coverage per bag depends on the desired thickness of the render and at the minimum recommended 6 mm thickness, coverage of approximately 2-3 m² can be expected.

Application Instructions

Substrates

Unitex® BBR 8.5 kg Render is applied to already coated and meshed Expanded Polystyrene wall cladding boards and especially the Unitex® factory coated product, Uni Base Board.

Substrate condition

Before application of any render, the surface must be clean, dry, cured and free of any dust and debris. This means that any loose or damaged substrate must be removed, or patched and repaired, prior to application of the base render. Ensure that the surface is clean and dry. All surfaces must be free of efflorescence, grease, oil, mould, dirt, dust, release agents, bond-breakers or other contaminants that may interfere with adhesion.

Adequate expansion joints are required to minimize cracking on the surface of the render. Location of the expansion joints is the responsibility of the Builder or Head Contractor. Unitex® recommends expansion joints to every elevation and between different substrates to allow for building movements and stresses. If such expansion joints are not provided, cracking due to movement of the substrate may occur. This is in no way indicative of faulty material. Rather it indicates sub-standard building practice.

All substrates must be dry before render is applied and conversely, all render surfaces must be dry before being over-coated. Unitex recommends testing surface dryness with a Moisture Meter (such as Protimeter) where the WME (Wood Moisture Equivalent) must be lower than 15 %.

Note: A test area of the complete Unitex® system must always be provided by the applicator for the Builder and Specifier approval.

Always contact Unitex® for specific substrate specifications.

Weather Conditions

If temperatures are less than 8 °C or greater than 30°C, Unitex® BBR 8.5 kg Render should not be applied to a wall.

Freshly applied Unitex® BBR 8.5 kg Render must be protected from rain, other sources of moisture and frosts for at least 48 hours.

Mixing



HEAD OFFICE
22 Park Drive
Dandenong VIC 3175

Phone: **(03) 9768 4900**
Fax **(03) 9768 4999**
www.unitex.com.au

NSW OFFICE
14 Artisan Road
Seven Hills NSW 2147

Phone: **(02) 9838 0911**
Fax **(02) 9838 9555**
www.unitex.com.au

RENDER WAREHOUSE
1346 North Road
Oakleigh South VIC 3167

Phone: **1800 RENDER**
Fax **(03) 9544 3620**
www.render.com.au

R40 Possible risk of irreversible effects
R43 May cause sensitization by skin contact
R48/20 Harmful: danger of serious damage to health by prolonged exposure through inhalation

Safety Phrases for Portland cement

S22 Do not breathe dust
S24/25 Avoid contact with skin and eyes
S36/37 Wear suitable protective clothing and gloves

The chemical composition of Portland cement is essentially oxides of various elements, the most prevalent being oxides of calcium Ca, silica Si, aluminium Al, iron Fe, titanium Ti, chromium Cr (mostly as insoluble Cr III but it is possible that water soluble Cr IV could be present at concentrations of less than 10 ppm). Trace amounts of oxides of magnesium Mg, potassium K and phosphorus P may also be present. As cement is a blended product, crystalline silica at levels less than 0.1 % may be present.

Not classified as dangerous goods according to the Australian Code for Transport of Dangerous Goods.
NON DANGEROUS GOODS

Manufacturer's Details

Company Unitex Granular Marble Pty Ltd
22 Park Drive
Dandenong, Vic. 3175
Australia

Telephone +61 3 9768 4900
Telefax +61 3 9768 4999
Website www.unitex.com.au

Date issued 01 November 2013

This information contained herein relates only to the specific material identified. Unitex Granular Marble Pty Ltd believes that such information is accurate and reliable as of the date of this Technical Data Sheet, but no representation, guarantee or warranty, expressed or implied, is made to the accuracy, reliability or completeness of the information. Unitex urges persons receiving this information to make their own determination as to the information's suitability and completeness for their particular application.